

The True Blue Solution for Concrete Moisture.



**Trust TEC® LiquiDam™ Moisture Vapor Barrier
for demanding moisture problems.**



With millions of square feet of successful flooring installations over concrete with high MVER, the LiquiDam™ formula is a proven moisture mitigation solution. Ideal for damp or new concrete, TEC® LiquiDam cures in as little as 4-5 hours, to allow for same-day flooring installation, and also provides a visual assurance of coverage during application. Additionally, shot blasting may not be required before application, and the 2-part system has zero VOC, to contribute to LEED® project points.

**Contact your local sales rep to request a demo.
Have a question? Visit TECQuestions.com.**



To learn more, visit TECSpecialty.com

See Reverse for More Information 



LiquiDam™ Penetrating Moisture Vapor Barrier

TEC® LiquiDam™ is a low viscosity, high penetrating, two-part 100% solids epoxy. It is specially formulated to be applied to damp or new concrete, as little as 48 hours old, with a moisture vapor emission rate (MVER) less than or equal to 25 lbs. per 1,000 ft² per 24 hours (0.12 kg/m² per 24 hours) or a maximum relative humidity of 100%. It is designed to reduce the MVER to less than 3 lbs. per 1,000 ft² per 24 hours (0.015 kg/m² per 24 hours).



⊘ Grinding or shot blasting may not be required*



One coat application



Fast drying formula allows for same-day installation

Features and Benefits

- Meets ASTM F3010 product requirements for moisture mitigation systems under resilient floor coverings
- Less than 0.10 Perm Rating (ASTM E96)
- Direct application onto green concrete up to 100% RH
- Shot blasting may not be required*
- Can be installed over burnished concrete
- Permeates to fill voids and gaps
- Same day flooring installation – cures within 4-5 hours
- Only one coat needed
- Zero VOC contributes to LEED® project points

Packaging

Two part system components (packaged in a carton) as follows:

Part A: .67 gallon (2.5 L) in two jugs inside a 2 gallon (7.57 L) pail

Part B: .33 gallon (1262 mL) plastic jug

US version - Product #15036204

Canadian version - Product #15036205



Conforms with LEED v4 low emitting interiors.
Compliant with (CDPH) Standard Method v1.2 VOC Emissions.

*On clean, sound concrete. Refer to the product data sheet for details.

Coverage

LiquiDam requires only one coat with a typical coverage rate of 150 ft² per blended gallon (3.7 m²/L). Coverage will vary depending on surface profile and porosity, ranging from 100-180 ft² per blended gallon (2.5-4.4 m²/L). The finished application must cover the substrate completely without any voids or pinholes to ensure moisture vapor suppression.

Technical Data

| In Use Performance | Typical Results |
|--|---|
| Percent Solids | 100% |
| Maximum Allowable Moisture Vapor Emission Rate | 25 lbs. per 1,000 ft² per 24 hours (0.12 kg/m² per 24 hours) |
| Adhesion (ASTM D7234) | 400-500 psi (2.76-3.45 MPa) (100% concrete failure) |

Physical Properties

| Description | |
|---|--|
| Pot Life | 25 minutes |
| Floor Installation Time [at 70°F (21°C), 50% RH] | 4-5 hours |
| VOC | Part A: 0 grams/liter Part B: 0 grams/liter |

Suitable Substrates

New or existing concrete with a maximum RH of 100% or MVER of 25 lbs. per 1,000 ft² per 24 hours (0.12 kg/m² per 24 hours).

▶ To learn more, visit TECspecialty.com



H.B. Fuller Construction Products Inc. | 1105 South Frontenac Street Aurora, IL 60504-6451



@TECInstallationSystems



tecinstitutionsystems



TECInstallationSystems



TEC Installation Systems